

Microprint

Wysokiej jakości karton z włókien wtórnych pozyskanych z recydingu.

Dane techniczne

Gramatura / Substance	Grubość / Caliper	Volumen / Bulk	Sztwność Taber (15°) / Taber stiffnes (15°)		Sztwność L&W (5°) / L&W stiffnes (5°)	
			MD	CD	MD	CD
g/m ²	μm	cm ³ /g	mNm	mNm	mNm	mNm
±5 %	±5 %	±5 %	±15 %		±15 %	
190	215	1.13	2.1	1.1	5.3	2.7
200	230	1.15	3.1	1.4	6.0	3.1
210	245	1.17	3.4	1.7	6.7	3.5
220	260	1.18	4.0	1.9	7.5	3.8
230	280	1.22	4.5	2.1	8.6	4.4
250	310	1.26	6.7	2.9	11.3	5.3
275	345	1.25	8.5	3.6	15.5	6.8
250	325	1.30	7.0	3.1	12.3	5.6
275	358	1.30	9.0	4.1	16.8	7.6
300	390	1.30	12.2	5.5	20.6	9.5
325	423	1.30	15.2	6.9	27.0	12.0
350	455	1.30	19.1	8.6	35.7	15.9
375	488	1.30	23.0	10.2	44.0	19.2
400	520	1.30	27.0	12.3	55.0	23.5
425	553	1.30	31.4	14.8	63.0	28.5
450	585	1.30	36.8	17.3	71.0	30.9
475	618	1.30	42.1	19.6	82.0	37.3
500	650	1.30	47.0	22.1	89.0	41.0
550	715	1.30	49.0	24.5	115.0	53.0