



Plastic Sheets



marpet 
PET SHEET

Product Guide

marpet-afs **marpet-gfs**
FLAT a-PET SHEET FLAT PET-g SHEET



Product Guide

Brett Martin is recognised around the world for the manufacture of a wide range of plastic sheet materials ideally suited for construction, engineering, print and display and a comprehensive range of plastic building products and materials. The established brand portfolio includes extensive sheeting, glazing and rooflight options in Polycarbonate, Acrylic, PVC, Foam PVC, aPET, PETg, SAN and Styrene and is continually extended and developed to include new product innovations.

With over 50 years of manufacturing experience and a renowned reputation for excellence Brett Martin export to five continents and over 70 countries affirming a commitment to innovation, product quality, performance and customer service.

Contents

1. Marpet FS PET Sheet	Page
General Overview	5
Marpet-a FS aPET	5
Marpet-g FS PETg	5
Marpet FS PET Product Range	5
2. Application Areas	
Design Versatility	7
Applications	7
3. Specification & Performance	
Material Properties	9
Mechanical Properties	10
Optical Characteristics	10
Chemical Resistance	11
4. Fabrication	
General guidance	13
Cutting and punching	13
Sawing	14
Drilling	15
Milling	15
Hinge effect	15
Laser cutting	15
5. Forming	
Cold forming	17
Hot line bending	17
Thermoforming	18
Blow moulding	19
Thermoforming Troubleshooting	19
6. Bonding & Fastening	
General guidance	21
Bonding with adhesive tape	21
Bonding with adhesive bonding agents	21
Welding	21
Mechanical fastening	21
7. Finishing	
Polishing	23
Decorating	23
8. Cleaning	25
9. Packaging and Storage	
Surface Protection	27
Storage & Handling	27
Safety	27
10. Installation	
Expansion Behaviour	29
Installation	29
Cold Curving	30
11. Important Notes	
Environmental Policy	32
Responsibility of End User	32
Appendices	
Appendix 1 Chemical Resistance	34

IMPORTANT NOTE ON SEMI-FINISHED MATERIALS

Since the end uses of semi-finished materials are so diverse it is the responsibility of each user of Brett Martin's Marpet-a FS aPET and Marpet-g FS PETg sheets to determine each material's suitability for their own particular use.

All the information is given in good faith but without commitment and warranty given or implied. Brett Martin accepts no liability for defects, loss or damage resulting from misuse, improper installation, inappropriate specification or any other factor beyond its control.

In accordance with our company's policy of continual product development, you are advised to check with your local Brett Martin representative to ensure that you have obtained the most up to date information.



Section 1

Marpet FS Sheet

Marpet FS Sheet	Page
General Overview	5
Marpet-a FS aPET	5
Marpet-g FS PETg	5
Marpet FS PET Product Range	5

General Overview

Brett Martin's Marpet FS PET sheet range includes Marpet-a FS and Marpet-g FS, high-quality, extruded, solid polyester sheets. Each material option possesses individual properties and performance capabilities which determine its suitability for a variety of end use applications.

MARPET-A FS APET

Marpet-a FS is high-quality, extruded, solid plastic sheet made of amorphous polyethylene terephthalate (aPET). No other plastic sheet offers its unique combination of mechanical, thermal and chemical properties. Combining exceptional quality, excellent transparency, impact strength, chemical resistance and fire performance, Marpet-a FS is ideal for applications which require its high performance characteristics and processability.

Its ability to cost effectively machine, cold bend and print lends Marpet-a FS particularly well to fabrication of items for the visual communications sector including point of purchase display stands, poster glazing and illuminated signage. Marpet-a FS may be thermoformed and hot line bent within a controlled temperature range to avoid crystallisation. Due to its superior strength and resistance to breakage Marpet-a FS is also equally suitable for safety equipment such as machine guards and visors. Its innovative combination of mechanical, thermal and chemical properties make Marpet-a FS a material that meets the highest demands in a wide range of flat and cold bent applications.

- Excellent optical clarity with 90% transparency
- Superior chemical resistance against cleaning agents, mineral oils and solvents
- High impact strength and resistance to breakage even at sub-zero temperatures
- Good scratch and scuff resistance
- Temperature range -20°C to + 60°C
- Suitable for cold bending
- Can be thermoformed and hot line bent within a controlled temperature range
- Excellent fire performance
- 100% recyclable

MARPET-G FS PETG

Marpet-g FS is a clear transparent thermoplastic (polyethylene terephthalate glycol) polyester flat sheet that offers excellent strength to weight ratio, outstanding optical clarity, superior chemical resistance, durability, good fire performance and is 100% recyclable. A key benefit of this material is its processability for fabrication. It is easy to shape and form into complex designs. Marpet-g FS provides an exceptional surface for screen and digital printing, and, the adhesion of secondary graphics.

These properties make Marpet-g FS the ideal product for a wide range of sign & display applications including point of sale equipment, signage, illuminated advertising signs, displays and graphic arts and is suitable for protective glazing applications including vending machines, interior safety glazing and office partition screens.

- Optically clear sheet with excellent light transmission
- Good impact strength
- No pre-drying before thermoforming
- Excellent thermoforming properties
- Exceptionally printability
- Reduced process time
- Chemical resistance
- Easily machined and fabricated
- Temperature range -20°C to + 60°C
- Excellent fire performance
- 100% Recyclable

MARPET FS PET PRODUCT RANGE

Standard Sheet sizes

Marpet-a FS aPET		
Dimensions	Thickness	Colour
2050x3050mm	2, 3 & 4mm	Clear
Marpet-g FS PETg		
Dimensions	Thickness	Colour
1250x2500mm	0.5, 0.75, 1 & 1.5mm	Clear
2050x3050mm	2, 3, 4, 5, 6, 8, 10 & 12mm	Clear

Minimum order quantities may apply. Special options are available, subject to request.



Section 2

Application Areas

Application Areas	Page
Design Versatility	7
Applications	7

Application Areas

DESIGN VERSATILITY

The Marpet FS PET range offers a choice of Marpet-a aPET and Marpet-g FS PETg clear transparent flat sheets. Each material offers distinct and unique properties which increase its suitability for specific end use applications.

APPLICATIONS

Product	Markets	Application	Key features
Marpet-a FS aPET	<ul style="list-style-type: none"> • Signage and display • Automotive • Transportation • Furniture • Industrial Manufacturing Equipment, Sports, Leisure & Consumer Goods • Building & construction 	<ul style="list-style-type: none"> • Document & poster holders, Display cabinets, Display shelving, Poster covers, Flat signs, Illuminated advertising, Price tags • Machinery guards and glazing, Industrial glazing, fume cupboards, Industrial trays • Advertising signs, Internal partitions and ceilings, DIY 	<ul style="list-style-type: none"> • Cold-curving • Chemical resistance • High impact resistance • No pre-drying for thermoforming
Marpet-g FS PETg	<ul style="list-style-type: none"> • Building & construction • Signage and display • Industrial • Furniture • Transportation • Manufacturing Equipment 	<ul style="list-style-type: none"> • Interior design - partitions, furniture, lighting elements • Displays - hotels, stores, industry, offices, exhibition, 3D POS items, booths - walls, ceilings, floors, counters, pillars, • Store fixtures - modular concepts, individual solutions • Flat signs, formed signs, • Machine guards, safety glazing (interior), vending machines, indoor glazing, medical equipment, bicycle helmets, dispensers • Refrigerators and cold storeroom equipment 	<ul style="list-style-type: none"> • Flat and arched applications, • Freedom of design, vacuum forming, transparency & colour uniformity • Easy digital and screen print, print finish • Thermoforming



Section 3

Specification & Performance

Specification & Performance	Page
Material Properties	9
Mechanical Properties	10
Optical characteristics	10
Chemical resistance	11

Specification & Performance

MATERIAL PROPERTIES

Property		Test Method	Marpet-a FS (aPET)	Marpet-g FS (PETg)
Physical	Density	ISO 1183	1.33g/cm ³	1.27g/cm ³
	Moisture absorption (24 hrs @ 23°C)	ISO 62-4	<0.2% by weight	<0.2% by weight
	Smell		Odourless	Odourless
	Water solubility	DIN 53122	Insoluble	Insoluble
Mechanical	Tensile Strength at Yield	ISO 527	56MPa	>50MPa
	Flexural Strength	ISO 178	86MPa	80MPa
	Modulus of elasticity	ISO 527	2420MPa	2100MPa
	Elongation at break	ISO 527	No breakage	No breakage
	Rockwell Hardness (R-Scale)		111R	115R
	Impact resistance (Charpy test, un-notched)	ISO 179	No breakage	No breakage
	Ball pressure hardness		117MPa	
Optical	Refractive Index	ASTM D-1003	1.578%	1.570%
	Light transmission	ASTM D-542	89%	89%
Thermal	Vicat Softening Temperature	ISO 306 (B)	75°C	82°C
	Thermal conductivity, K	DIN 52612	0.25 W/m°C	0.2 W/m°C
	Heat deflection temperature (1.8MPa)	ISO 75-2	68°C	68°C
	Heat deflection temperature (0.45MPa)	ISO 75-2	72°C	72°C
	Thermal expansion coefficient	ISO 75-2	0.06mm/m°C	0.068mm/m°C
	Service Temperature Range		-20 to +60°C	-20 to +60°C
	Volume resistivity	IEC 60093	10 ¹⁵ Ωcm	10 ¹⁵ Ωcm
	Dielectric constant (1kHz)	IEC 60250	3.4	2.60
	Surface Resistivity	IEC 60093	10 ¹⁶ Ω	10 ¹⁶ Ω

MECHANICAL PROPERTIES

The mechanical behaviour of Marpet FS PET is characterised especially by its modulus of elasticity and impact resistance.

The modulus of elasticity is a measure of the rigidity or elasticity of a material. It denotes the relationship between the force exerted on the sheet in the tensile test and the resulting elasticity. The modulus of elasticity depends on the test conditions and temperature.

At room temperature elastic modulus is around 2400 MPa for Marpet-a FS and 2100MPa for Marpet-g FS.

Materials with a higher modulus of elasticity (> 2800 MPa) such as unmodified acrylic or quartz glass are more brittle – at higher stressing they break more easily. Those with a low modulus of elasticity (> 1800 MPa) become soft and easy to shape. Marpet-a FS and Marpet-g FS possess a modulus of elasticity that permits withstanding of sudden impacts.

Marpet-a FS and Marpet-g FS exhibits no fractures in the flexural impact test (Charpy) and is highly impact resistant.

Minimal bending radius = 150 x sheet thickness

OPTICAL CHARACTERISTICS

Transmission and haze to ASTM D 1003.

Light transmission, haze and clarity are interconnected terms. They can be classified under the collective term “transparency”.

Impinging rays of light are divided into reflected, absorbed, deflected (scattered) and penetrating rays. The light that penetrates the sheet is called total transmission. It is divided into direct light transmission and glaze.

The total transmission is the relationship of the total transmitted light to the incident light quality; it is reduced through absorption and reflection. The haze is the percentage part of the transmitted light that is scattered from the luminous beam on average by more than 2.5°.




Fig. 1: Light diffusion

	Method	Marpet -a FS	Marpet -g FS	Unit
Reflective index nD at 589 nm (3mm sheet)	DIN 53491	1.578	1.570	-
Transmission (3mm sheet)	DIN 5036	89	89	%
Haze (3mm sheet)	ASTM 1003	<1	<1	%

CHEMICAL RESISTANCE

Chemicals can affect the strength, flexibility, surface appearance, colour, dimensions or weight of plastics. The basic modes of interaction which cause these changes are:

- chemical attack on the polymer chain, with resultant reduction in physical properties
- physical change, including absorption of solvents, resulting in softening and swelling of the plastic;
- stress cracking from the interaction of an incompatible chemical.

Other factors affecting chemical resistance include pressure and internal or external stresses, length of exposure, temperature and concentration of the chemical.

Marpet-a FS aPET

Marpet-a FS aPET sheet is characterised by its high stress cracking resistance. Because of its very good chemical resistance, Marpet-a FS can be installed with all standard sealing strips and materials, e.g. APTK (EPDM), TPE, silicone joint filler, butyl adhesive tapes and soft PVC tapes.

Marpet-a FS sheet is resistant to most acids, salts, alcohols, hydrocarbons and solvents, and is especially resistant to cleaning agents and glass cleaners containing alcohol. Environmental influences such as acid rain, soot and diesel fumes, salt-containing air and seawater do not affect Marpet-a FS.

Even graffiti can be removed from Marpet-a FS by using e.g. acetone-free and benzene-free solvent cleaners or diluting agents. Its optical and mechanical properties are not impaired.

Marpet-g FS PETg

Marpet-g FS PETg sheet has satisfactory resistance to mineral and vegetable oil, turpentine, detergents, alcohols: ethanol and methanol, petrol glycerine. Contact should be avoided with acetone, ammonia and toluene.

Mixing and/or dilution of certain chemicals may result in reactions that produce heat and can cause product failure. Pre-test your specific usage and always follow correct safety procedures. (See Appendix 1)



Section 4

Fabrication

Fabrication	Page
General Guidance	13
Cutting and punching	13
Sawing	14
Drilling	15
Milling	15
Hinge effect	15
Laser cutting	15

Fabrication

GENERAL GUIDANCE

Tools

Marpet-a FS and Marpet-g FS sheets may be machined using standard tools used for metal and woodworking. Carbide-tipped tools are recommended. It is important to use sharp cutting tools with the correct angles.

Cooling

Cooling is not necessary during the normal machining of Marpet-a FS and Marpet-g FS sheets. If overheating does occur during machining the area should be cooled with water or compressed air. The use of oil emulsions and cutting oils is not recommended as these may contain chemicals to which aPET and PETg are not resistant and could result in stress crack formation.

Dimensional accuracy

At 0.04 - 0.060 mm/mK Marpet-a FS and Marpet-g FS coefficient of linear expansion is significantly higher than for metal or glass. It is imperative that material dimensions are checked at room temperature. Shrinkage of around 3-6 % (dependant on thickness) will occur when the material is heated above the glass transition temperature (81°C) for the first time.

Protective film

Marpet FS PET sheets have a protective film on both sides to ensure that the smooth surfaces are not damaged during transport and machining. The surface of Marpet-a FS aPET sheet has a green film and a white film underside. The surface of Marpet-g FS PETg sheet has a blue film and a white film underside. The protective film should be left in place during machining.

Marking

Drill holes, cut edges and so on should be marked on the protective film using a soft pencil or felt-tip pen. Marking tools should not be used as the tracing mark has a notching effect, and a higher load at this point may cause the sheet to break.

CUTTING AND PUNCHING

Marpet FS sheets up to 1.5 mm thick may be cut and punched. Generally the thicker the sheet, the poorer the quality of the cut and the greater the risk of cracking.

For best results use a sharp shearing tool with a wedge angle of max. 30°, with clearance between the tool and the cutting surface of 0.01 to 0.03 mm (see Figs. 2 & 3).




Fig. 2: Clean cut edges




Fig. 3: Cutters for punching

For clean, smooth cut edges it is recommended to saw or mill Marpet-a FS and Marpet-g FS sheets >1.5 mm in thickness. When punching close-tolerance holes make allowance for shrinkage if machining is to be followed by heat treatment of over 80 °C. The hole should be measured approx. 5 % larger than actually required. The bigger the hole and the thicker the sheet, the lower the tendency for the sheet to shrink. Good results are obtained using symmetrically bevelled shearing tools.

For punching/shearing Marpet-a FS and Marpet-g FS sheets that are more than 1.5 mm thick use an asymmetrically bevelled blade. To cut right angles, blades on one side bevelled with a wedge angle of 30° should be used. The back-up pad (polyamide or high density polyethylene) should be in place and centred with the punching tool to achieve clean cut edges.

SAWING

Hand saws

A standard hand saw with fine spacing between the teeth may be used to cut Marpet-a FS and Marpet-g FS sheets. When sawing by hand it is likewise better to use blades that are narrower and have more set.

Circular saws

A circular saw is the easiest way to cut Marpet-a FS and Marpet-g FS sheets. Carbide-tipped circular saw blades produce the cleanest cuts. The tooth pitch of the blade varies depending on sheet thickness (fine for thin sheets, too coarse for thicker materials). Remove swarf and shavings from the cutting surface to avoid potential damage to the protective film and sheets.

For sheets <1.5 mm use a thick underlay board or a pair of shears instead of a circular saw.

To cut curved or formed parts and irregular shapes use a band saw. Work on a solid cutting surface to achieve a clean cut edge. A blade with a wide tooth pitch is required when working with thicker sheets. For higher quality cut edges, circular saws or routers achieve a better result than band saws.




Fig. 4: Band Saw




Fig. 5: Circular saw blade

TROUBLE-SHOOTING

Fused cut edge:

- Check tool sharpness
- Check cutting speed and reduce if necessary
- Check rate of advance and reduce if necessary
- Cool if necessary

Notched cut edge:

- Check tool sharpness
- Check tool geometry
- Check cutting speed and increase if necessary
- Improve cutting surface (use an underlay if necessary)

STANDARD SETTINGS FOR SAWING

	Band saw	Circular saw
Clearance Angle 'a'	20 - 40°	10 - 30°
Rake angle 'y'	0 - 5°	5 - 15°
Cutting speed (m/min)	600 - 1000	1000 - 3000
Tooth pitch 't' (mm)	1.5 - 3.5	2 - 10

(see Figs. 4 & 5)

DRILLING

Standard metal working drills are suitable for machining Marpet-a FS and Marpet-g FS. Ensure the drill bits are sharp. Cooling during drilling is generally not necessary. For large drilling depths use water or compressed air and/or regularly withdraw the drill from the hole to reduce heat and remove shavings.

Oil/water emulsions or cutting oils should not be used when drilling through Marpet-a FS and Marpet-g FS sheets. Standard circle-cutting equipment (e.g. circle cutters or compass saws) is suitable for large-scale drilling.

The drill holes should be smooth and as free as possible of notches or rough areas to ensure secure fastening.




Fig. 6: Drills for Marpet-a FS and Marpet-g FS sheets

Recommended angles for drilling (see Fig. 6):

Point angle ϕ	110° - 130°
Helix angle β	19° - 40°
Cutting speed	30 - 60 m/min.
Feed	0.1 – 0.3 mm/Rev.

A distance of at least 2 times the diameter of the drill hole but minimum of 10mm should be allowed between the drill hole and the edge of the sheet.

MILLING

Marpet-a FS and Marpet-g FS sheets are easy to process using milling machines. The choice of milling machine depends on the type of machining required. Ensure that your tool has good chip clearance and sharp cutters.

HINGE EFFECT

Marpet-a FS has a very high level of fatigue resistance, creating scope for a diverse range of hinge effects. By pressing with a blunt blade, pre-punching or milling, it is possible to create the bent edges that may be required on the inside. Sheets of up to 1.5 mm in thickness can be crease line folded or pre-punched whilst V-shaped milling should be used for thicker sheets. These edges are permanently moveable, on a par with paper or cardboard flaps.




Fig. 7: Hinge effect

LASER CUTTING

When cutting intricate shapes and contours, lasers are more suitable. Marpet-a FS and Marpet-g FS sheets should be annealed following laser cutting. Thicknesses above 3mm can be laser cut although the finished edge will be slightly rough and discoloured. A glossy edge can be achieved from flame polishing depending on the sheet thickness.

Experimentation is needed to achieve the desired result. An effective extraction system is necessary to remove the smoke, vapours and other combustion gasses formed during cutting. Laser cutting aPET and PETg will produce noxious gases. It is strongly recommended that all combustion gases formed during cutting are eliminated before removing the part and that only thin sheets (less than 1 mm) be laser cut.



Section 5

Forming

Forming	Page
Cold forming	17
Hot line bending	17
Thermoforming	18
Blow Moulding	19
Thermoforming Troubleshooting	19

Forming

COLD FORMING

Cold curving

Marpet-a FS and Marpet-g FS sheets may be cold curved with a minimum radius of 150 times sheet thickness. Thermoforming is recommended for smaller radii.

Minimum radius $\geq 150 \times$ sheet Thickness

Cold bending – press break machine

Marpet-a FS and Marpet-g FS sheets can be cold formed. The best results are achieved with a rotating bending machine. Cavity folding is possible up to a thickness of 3 mm.

Bending Marpet-a FS and Marpet-g FS sheets up to 3mm thick may be performed without heating. For a sheet 3mm thick a 90° may be achieved using conventional metal folders.

The relaxation immediately following the cold folding process means that the sheet has to be overstretched by approximately 25°. The internal and external stress levels take a few days to become balanced with the parts, only then taking on their final shape.

The sheet should be folded parallel to the extrusion direction marked on the masking. Bear in mind that cold brake forming places high stresses on the edge areas of the material. Avoid the use of aggressive chemicals, particularly with cold brake formed and cold bent parts.

The use of cold folding should be restricted to Marpet FS sheets with low thickness.

HOT LINE BENDING

To hot line bend Marpet-a FS and Marpet-g FS sheet, locally heat the area to 100 °C using IR heaters or heating elements in a linear manner (see Fig. 8). When the optimum temperature is reached remove the sheet from the heating element, fold, place in the mould and clamp into position until the material cools and becomes rigid. This will achieve the required shape. The protective film does not need to be removed.

If using one-sided heating, the sheet must be turned over several times to guarantee even heating on both sides. With sheet thicknesses of 2 mm or more and

when producing large numbers of units, it is best to heat both sides of the sheet simultaneously using a sandwich heating appliance. Various bending radii can be achieved by adjusting the heating width (see Fig. 9). Do not exceed a minimum bend radius of 3 times the sheet thickness.




Fig. 8: Hot line bending




Fig. 9: Heating zone

Example:

$$\begin{aligned} \text{For 3mm } 45^\circ \text{ angle} \\ x &= 0.026 \times 3 \times 45 \\ &= 3.51\text{mm} \end{aligned}$$

IMPORTANT Excessively high temperatures can lead to crystallisation and whitening in the heated area for Marpet-a FS aPET. Local heating may also create stresses in the finished part. Care should be taken when using chemicals with bent formed parts.

THERMOFORMING

Marpet-a FS and Marpet-g FS sheets may be thermoformed even at low temperatures (100 to 160°C). However, even at these temperatures Marpet-a FS sheets may crystallize resulting in whitening. To avoid crystallisation ensure short heating times and rapid cooling of the moulded part to preserve the material's transparency. Trials should be conducted in advance.

Pre-drying

It is not necessary to pre-dry Marpet-a FS and Marpet-g FS sheets prior to thermoforming.

Heating during thermoforming

Marpet-a FS and Marpet-g FS sheets should be heated evenly as part of a controlled process to a temperature of 100 to 160 °C. More precise results are achieved at the upper end of the forming temperature range. High temperatures can result in crystallization of Marpet-a FS sheets.

As Marpet FS sheets cool quickly, heat sheets whilst on the forming machine and not in separate ovens.

For best results use two sided IR heating systems which provide a more even and faster heating of the material for shorter, more economical cycle times. This process also reduces the risk of crystallisation for Marpet-a FS sheets. It is important to cool Marpet-a FS quickly using compressed air until the parts are completely cooled.

Heating with IR or ceramic elements provide the best heating sources for Marpet-g FS sheets. One side heating is not recommended for sheets of 3mm or above.

Marpet-a FS and Marpet-g FS shrink by 0.4% cooling.

IMPORTANT Excessively high temperatures can lead to crystallisation and whitening in the heated area for Marpet-a FS aPET. Local heating may also create stresses in the finished part. Care should be taken when using chemicals with bent formed parts.

Thermoforming tools:

Depending on the size of the production series and desired surface quality, tools made from different materials can be used. Please note that the material selected will influence cooling time and surface properties. The mould should be sufficiently rounded. Marpet-a FS and Marpet-g FS sheets effectively reproduce detail. We recommend not polishing the surface of the mould but slightly matting it to avoid impressions on the formed part. When constructing forming moulds, allowance should be made for shrinkage of 0.4%. Special materials are available for producing porous forming tools without vents.

Male and female tools

The decision on whether to use a male or female tool depends on the application. To achieve a better surface quality on the outer side of the finished part, use of a female tool is recommended to attain greater detail.




Fig. 10: Male and Female thermoforming tools

BLOW MOULDING

Blow moulding is used to form domes. This technique involves working with air pressure, whilst the thermoforming process is carried out in a vacuum. To produce the moulding, the sheets should be evenly heated. At a sheet temperature of approx. 80 °C, the part retains its desired shape and can be removed.

THERMOFORMING TROUBLESHOOTING

Problems	Possible Causes	Solution	Hot Bending	Thermo-Forming	Blow Moulding
White coloration	Sheets too hot	Reduce heating	•	•	•
	Production cycle too long	Shorten cooling period		•	•
Badly formed parts	Sheets too hot	Reduce heating	•	•	•
	Production cycle too long	Shorten cooling period		•	
	Vacuum speed too fast	Limit vacuum		•	
	Sharp edges	Round off edges		•	
Thin edges	Sheets too small	Use larger sheets		•	
Wave formation	Uneven heating	Check heating surface		•	
	Too small distance between moulds	Increase min. distance between parts		•	•
	Vacuum too fast	Limit vacuum		•	•
	Sheet surface too large	Distance between clamp and tool <50mm		•	
Reduced details	Insufficient vacuum or compressed air	Increase vacuum or compressed air to check for lack of tightness		•	•
	Sheet temperature too low	Increase heating		•	
Moulding sticks to mould	Mould too hot	Reduce mould temperature		•	
	Release angle too small	Increase release angle		•	
Impressions	Mould surface too smooth	Slightly matt tool		•	
	Sheet temperature too high	Reduce heating/heating time		•	
Surface defects	Dust on sheet or mould	Clean with ionised/compressed air		•	•
Uneven finished parts	Heating/cooling	Check for draughts; check heating		•	•
	Release too fast	Sufficient cooling of part		•	
Tears or cracks	Excessive stress	Slow heating, heat large surface area	•	•	•



Section 6

Bonding & Fastening

Bonding & Fastening	Page
General guidance	21
Bonding with adhesive tape	21
Bonding with adhesive bonding agents	21
Welding	21
Mechanical fastening	21

Bonding & Fastening

GENERAL GUIDANCE

Marpet-a FS is difficult to bond due to its high chemical resistance therefore bonding using adhesive tape, mechanical fastening and welding are recommended instead. Marpet-g FS can be bonded to itself or to other materials using commercially available adhesives suitable for polyester. It is recommended to check/test suitability of the adhesive with polyester prior to any application.

BONDING WITH ADHESIVE TAPE

Double-sided adhesive tape (acrylic based) may be used for rapid bonding. These tapes are elastic and adhere well to Marpet FS PET sheets. They are particularly suitable for bonding thin Marpet FS sheets to other plastics, glass or metal.




Fig. 11: Bonding using adhesive tape

Tips for good bonding:

- Clean the area with isopropyl alcohol.
- Carefully apply the adhesive tape.
- Use a roller to apply even pressure to remove any air bubbles and improve adhesion.
- Adhesives manufacturer's guidelines and safety advice must be observed.

BONDING WITH ADHESIVE BONDING AGENTS

Only a few industrial adhesives prove suitable for bonding Marpet-a FS e.g. instant products and/or cyanoacrylate, 2-component polyurethane products. Solvent adhesives could be used with Marpet-g FS for bonding small and plane surfaces. Stresses in the sheet or in the parts combined with the use of bonding agents may result in crack formation.

WELDING

Ultrasonic and friction welding are possible options but mechanical fastening and bonding are preferable. Information is available from the equipment manufacturer.

MECHANICAL FASTENING

Due to its good impact resistance, Marpet FS PET can be fastened mechanically using any method. Up to a thickness of 1.5 mm it can be nailed, tacked or riveted. When using screws, opt for screws with a cylindrical head to bond various parts further and avoid any with countersunk heads, as these can cause cracking (Fig. 12). Drill holes should be measured to allow for expansion and shrinkage (Fig. 13).

All plastic screws are suitable. When using metal screws a suitable plastic washer is required. Avoid over-tightening screws. Use a through bolt rather than cutting a thread in the sheet.




Fig. 12: Avoid screws with countersunk heads




Fig. 13: Mechanical fastening



Section 7

Finishing

Finishing	Page
Polishing	23
Decorating	23

Finishing

POLISHING

Flame Polishing

Taking care not to overheat and crystallise the material, an experienced flame polisher can achieve excellent results with propane, butane or other types of gas burner. Cracks may appear in the polished area in the long term.

Buffing

Using alkali-free polishing pastes, medium-density polishing wheels with a peripheral velocity of 20 to 30 m/s can be used to polish Marpet-a FS and Marpet-g FS sheets. A clean polishing wheel without polishing paste is then used to complete the polishing process. Large-surface polishing should be avoided.

DECORATING

Marpet-a FS and Marpet-g FS sheets should be cleaned before secondary processing, such as coating, screen printing or thermoforming to remove any loose particles of dirt or dust from the surface. Use ionized air for best results. (See Section 8 on Cleaning).

Screen printing

Marpet-a FS and Marpet-g FS may be easily printed with standard screen printing equipment and inks suitable for thermoplastic polyesters (PET). The ink manufacturer's recommendations should be followed.

Digital printing

Marpet-a FS and Marpet-g FS sheets can be printed with UV cured inks. The short-term UV radiation has no impact on the physical properties. Due to the chemical and solvent resistance of Marpet-a FS some ink systems may have difficulty in obtaining a good bond to the sheet surface. In common with other plastic materials, special printing inks are usually required since the ink does not penetrate the plastic as it does paper and cloth. As the ink is not absorbed into the plastic, it may be subject to abrasion. However, this can be minimised by the application of a light coat of clear lacquer over the printing. It is recommended that a preliminary test with the inks should be performed to confirm quality of results. The maximum application temperature of 50°C should not be exceeded during the drying process.



Section 8

Cleaning

Cleaning	Page
Cleaning	25

Cleaning

Dust can settle on the surface of the Marpet-a FS and Marpet-g FS sheets, particularly as a result of electrostatic charging. Dusty surfaces can be easily wiped clean with a damp, soft cloth or sponged with warm water containing some washing-up liquid. Before secondary processing of Marpet FS PET sheets, particularly when thermoforming or printing, remove any loose particles of dirt or dust on the surface by blowing with ionized air.

Grease and oil spots can be simply and quickly removed with ethanol or isopropanol because Marpet-a FS and Marpet-g FS are not attacked by these solvents.

For thorough cleaning, use a non-abrasive detergent such as washing up liquid. Razor blades or other sharp tools, abrasive or strongly alkaline detergents, solvents, leaded benzene and carbon tetrachloride should not be used.

The only way to achieve effective cleaning without streaks is to use a microfiber cloth that is simply dampened with water. In the case of a greater build-up of dirt or greasy stains in particular, use acetone – and benzene-free solvent cleaners or thinners. The optical and mechanical properties will remain unaffected by these cleaners. Some spray paint and graffiti can also be removed in this way.

Splashes of dye, grease etc. may be removed before curing using a soft cloth soaked in ethyl alcohol or isopropyl alcohol.



Section 9

Packaging and Storage

Packaging and Storage	Page
Surface Protection	27
Storage & Handling	27
Safety	27

Packaging and Storage

SURFACE PROTECTION

All Marpet-a FS and Marpet-g FS sheets are covered by a protective polyethylene film. This surface protection is applied to two sides of the sheet and can be removed easily.

All Marpet-a FS and Marpet-g FS sheets are stacked on pallets at the end of the production line. The pallets are covered with stretch-wrap film and strapped to ensure they are received by the end user in pristine condition. The sheets should be similarly protected or packaged at all stages of process to ensure the quality of finished items.

STORAGE & HANDLING

Marpet FS sheets are best stored indoors, away from direct sunlight, in a cool dry store under ambient conditions.

The temperature of uncovered stacked sheets in direct sunlight can rise to levels which will be detrimental to the material: the presence of moisture between sheets can add to damage. Do not store indoors close to heat sources, for example, radiant heaters or boilers.


Sheets, whether stored indoors or outdoors, should be laid horizontally on a flat clean surface, for example, a solid topped pallet or wooden sheet raised from the floor or ground. Under the total weight of sheet loaded on to it, this support must not distort, or distortion of the sheet could occur during longer storage periods. Standing sheets on ends or sides, even for short periods, should be avoided.

Where storage outdoors cannot be avoided, at all times the stack of sheets should be completely enclosed within a reflective waterproof cover, placed over wooden battens on top of the stack to avoid contact with the sheet surface. The cover should be secured to protect the stack against sun, wind and rain and the stack should be ventilated to avoid heat build-up.

Marpet FS PET is a relatively flexible material but, if lifted or carried incorrectly, sheets can be stressed beyond their flexible limits and cracked. Sheets and cut panels should not be dragged off a stack but lifted

up directly and set down directly. Surfaces on which sheets are set must be clean to avoid damage.

When carrying, sheets should be turned on edge and held top and bottom. It will require more than one person to carry a large sheet or panel. Particular care should be taken with panels which have been processed, for example, screen printed.



SAFETY

Marpet-a FS and Marpet-g FS are rigid polyester sheets. These materials are not subject to the laws governing the use of dangerous materials or chemicals and meets the requirements of the RoHS and WEEE directives of the European Union on the restriction of certain hazardous substances.



Section 10

Installation

Installation	Page
Expansion Behaviour	29
Installation	29
Cold Curving	30

Installation

EXPANSION BEHAVIOUR

When measuring and installing Marpet-a FS and Marpet-g FS, the thermal expansion of the material should be taken into account, as with other plastic sheets.

Ensure that the sheet can expand sufficiently in hot and moist conditions and can contract sufficiently in the cold and dry.

The following table provides a comparison of the coefficients of expansion of various materials.

Material	$\times 10^{-6} K^{-1}$
Marpet-a FS (aPET)	approx. 68
Marpet-g FS (PETg)	approx. 60
Acrylic	approx. 70
Polycarbonate	approx. 65
Aluminium	approx. 22
Steel	approx. 13
Glass	approx. 0.8

The table shows that plastic sheet expands and contracts under the influence of temperature. These properties of the plastic must be taken into account when measuring and fitting the sheet.

Generally, 3.5mm/m expansion allowance will cover most applications.




Fig. 14: Expansion behaviour

INSTALLATION

Linear securing

The preferred method of installing Marpet-a FS and Marpet-g FS either in large flat sheets or as cold curved sheets is to use a profile system.

Linear securing ensures a uniform spread of weight in the supporting construction. The contact pressure must not be so high that it prevents allowance for expansion or prevents the sealing profiles from working. Contact pressure that is too low would not ensure water-tightness and the sheet would not be properly secured.

The correct contact pressure can be produced, as shown here, with prefabricated spacer sleeves or with screws with limited thread length.

The allowance for expansion of the sheets is absorbed by the flexing of the sealing profiles because of its very good chemical resistance. Marpet-a FS and Marpet-g FS can be installed with all commercially available sealing profiles.




Fig. 15: Installation

Point Securing

Marpet FS sheets can be point secured for small areas, using machine screws. Self-tapping screws may only be used with washers and/tension rings or spring clips.

With screw connections the drill holes should be at least 50% larger than the diameter of the screws so that tension-free absorption of movement is possible. For interior applications, the drill holes should be at least 1mm larger than the screw diameter. Slits and cut-outs may be advisable.

Distance from edge:
2x diameter of hole, but min. 10mm

COLD CURVING

Because of its outstanding elasticity, Marpet-a FS and Marpet-g FS sheets are ideal for cold curving.

The performance of the sheet is fully retained provided the sheet remains above the minimum bending radius.

The minimum bending radius is calculated according to the following formula:

Minimum bending radius = 150 x sheet thickness

Sheet thickness (mm)	Min. Curving radius (mm)
1	150
1.5	225
2	300
2.5	375
3	450
4	600
5	750
6	900




Fig. 16: Minimum bending radius



Section 11

Important Notes

Important Notes	Page
Environmental Policy	32
Responsibility of End User	32

Important Notes

ENVIRONMENTAL POLICY

Brett Martin Limited is committed to ensuring that high standards of environmental performance are maintained at all the Company's sites. The Company will continue to operate in such a way as to reduce any adverse effects on the environment arising from our activities, to a minimum and to consider the environment and the well-being of future generations in all Company policy decisions.

The Company will develop and implement activities which make efficient use of energy and raw materials and reduce emissions to earth, air and water, wherever practicable.

The Company will design our products to meet society's standards for the protection of health and the natural environment and, to this end, it is the policy of the Company continually to develop and refine systems of planning, organization and control and to continue to strive for improvements in plant and technology.

The Company will promote the correct use of our products to minimise pollution and operate a policy where re-use and recycling is of any waste material, both in-plant and by external users, is encouraged and implemented as far as possible.

Furthermore the Company accepts that all employees have a responsibility for minimising harm to the environment and will continue a process of continuous learning and development, allied to systematic training and information, to improve employee awareness of environmental principles.

RESPONSIBILITY OF END USER

The information contained in this publication is based on current knowledge and is in our opinion reliable. However the correctness of this information cannot be guaranteed for every application and for the results arising from their use.

The user/processor is always responsible for ensuring that the materials and processes are appropriate, cost effective and suitable for the intended purpose and location and they comply with laws and regulations.

Technical knowledge and skills as customary in trade and industry, a normally developed capacity to make judgements as well as knowledge and observance of the applicable regulations appertaining to work, safety and hygiene are assumed.



Appendices

Appendices	Page
Appendix 1 – Chemical Resistance	34

Appendix 1

CHEMICAL RESISTANCE

The data below concerning the chemical resistance of Marpet FS PET has been obtained from publically available data sources. The data should be treated with caution and should only be regarded as an indication of the chemical resistance since the resistance performance can be affected by many factors, such as temperature, concentration, and whether the samples are under stress. It is also difficult to predict the resistance against compounds containing several different chemicals.

Chemical Resistance Marpet-a FS aPET		
Chemical	Concentration	Amorphous PET
Acetic Acid	40% aq Glacial	Unaffected Some attack
Acetic Anhydride		Unsatisfactory
Acetone		Unsatisfactory
Aluminium Sulphate	Solid	Unaffected
Ammonia	10% aq & 0.88 SG aq	Unsatisfactory
Ammonium Chloride	Solid	Unaffected
Ammonium Persulphate	Solid	Unaffected
Ammonium Sulphate	Solid	Unaffected
Amyl Acetate		Some attack
Amyl Alcohol		Satisfactory
Amyl Methyl Ketone		Some attack
Aniline		Unsatisfactory
Anthraquinone	Solid	Unaffected
Barium Chloride	Solid	Unaffected
Benzene		Unsatisfactory
Benzoic Acid	Solid	Unaffected
Benzyl Acetate		Unsatisfactory
Benzyl Alcohol		Unsatisfactory
Benzyl Benzoate		Some attack
Butyl Acetate		Unsatisfactory
Butyl Alcohol		Unaffected
Butyl Lactate		Satisfactory
Butyl Stearate		Unaffected
Calcium Hypochlorite	Solid	Satisfactory

Chemical	Concentration	Amorphous PET
Camphor	Solid	Unaffected
Camphorated Oil		Satisfactory
Carbon Tetrachloride		Satisfactory
Castor Oil		Unaffected
Cetyl Alcohol	Solid	Unaffected
Chloral Hydrate	Solid	Unsatisfactory
Chlorobenzene		Unsatisfactory
Chloroform		Unsatisfactory
Chromic Acid	Plating solution	Unsatisfactory
Citric Acid		Unaffected
Citronellol		Satisfactory
Cupric Sulphate	Solid	Unaffected
Cyclohexane		Unaffected
Cyclohexanone		Unsatisfactory
Cyclohexanol		Unaffected
Diacetone Alcohol		Unaffected
Di-alkyl Phthalate		Unaffected
Di-butyl Phthalate		Unaffected
Di-nonyl Phthalate		Satisfactory
Di-octyl Phthalate		Unaffected
Dimethyl Formamide		Unsatisfactory
Dioxane		Unsatisfactory
Dipentene		Satisfactory
Di-1-phenyl Ethanol		Some attack
2-Ethoxy Ethanol		Satisfactory
Ethyl Acetate		Unsatisfactory
Ethyl Alcohol		Unaffected
Ethyl Benzene		Some attack
Ethyl Digol		Unaffected
Ethylene Chlorohydrin		Unsatisfactory
Ethylene Dibromate		Unsatisfactory
Ethylene Dichlorate		Unsatisfactory
Eugenol		Unsatisfactory
Ferric Nitrate	Solid	Unaffected
Formaldehyde	40% W/Waq	Unaffected
Formic Acid	3% aq & 30% aq	Satisfactory
Furfuryl Alcohol		Unsatisfactory
Geranoil		Satisfactory
Glycerine		Unaffected

Chemical	Concentration	Amorphous PET
Glycol		Unaffected
Hydrobromic Acid	50% aq	Unaffected
Hydrochloric Acid	10% aq	Satisfactory
Hydrofluoric Acid	60% aq Conc	Some attack Unsatisfactory
Hydrogen Peroxide		Unaffected
Hydroquinone Solid		Unaffected
Isopropyl Alcohol		Unaffected
Lanoline		Unaffected
Linalol		Satisfactory
Linseed Oil		Satisfactory
Lubricating Grease		Unaffected
Oil		Unaffected
Magnesium Chloride	Aq Solution	Satisfactory
Maleic Acid	25% 50% aq	Some attack Satisfactory
Mercuric Chloride	Solid	Unaffected
Mercury		Unaffected
2-Methoxy Ethanol		Some attack
Methyl Alcohol		Unaffected
Methyl Cyclohexanol		Unaffected
Methyl Ethyl Ketone		Unsatisfactory
Methyl Methacrylate		Some attack
Methyl Salicylate		Unsatisfactory
Mathylene Chloride		Unsatisfactory
Mineral Oil		Unaffected
Naphtha	Crude Solvent	Unaffected Satisfactory
Nitric Acid	10% aq	Satisfactory
n- Octane		Unaffected
Olive Oil		Satisfactory
Oxalic Acid	Solid Solution	Unaffected Satisfactory
Paraffin	Medicinal	Unaffected
Paraffin Oil		Unaffected
Petrol		Satisfactory
Petroleum Ether		Unaffected
Phenol		Unsatisfactory
Pinene		Satisfactory
Potassium Bromide	Solid	Unaffected
Potassium Chromate	Solid	Unaffected

Chemical	Concentration	Amorphous PET
Potassium Cyanide	Solid	Unaffected
Potassium Dichromate	Solid	Unaffected
Potassium Hydroxide	1% aq & 10% aq	Unsatisfactory
Potassium Permanganate	Solid	Some attack
Propionic Acid		Unsatisfactory
Propyl Alcohol		Unaffected
Propylene Glycol		Unaffected
Salicylic Acid	Solid	Unaffected
Sodium Bicarbonate	Solid	Unaffected
Sodium Borate	Solid	Unaffected
Sodium Bromide	Solid	Unaffected
Sodium Carbonate	Anhydrous & 2.5% aq	Unaffected
Sodium Chloride	1% aq 10% aq	Unaffected Satisfactory
Sodium Cyanide	Solid	Unaffected
Sodium Hydroxide	1%aq & 10%aq	Unsatisfactory
Sodium Nitrate	Solid	Satisfactory
Sodium Phosphate	Solid	Unaffected
Sodium Sulphite	Solid	Satisfactory
Sodium Thiosulphate	Solid	Unaffected
Stearic Acid	Solid	Satisfactory
Sulphur	Solid	Unaffected
Sulphuric Acid	3% aq 30%aq	Some attack Satisfactory
Tartaric Acid	Solid	Satisfactory
Tetrahydrofuran		Unsatisfactory
Tetralin		Unaffected
Toluene		Satisfactory
Transformer Oil		Satisfactory
Trichloroethyl Phosphate		Unaffected
Trichloroacetic Acid		Unsatisfactory
Trichloroethylene		Unsatisfactory
Triethanolamine		Unsatisfactory
Vinegar		Satisfactory
Xylene		Satisfactory
Zinc Chloride	Solid	Satisfactory

Chemical resistance Marpet-g FS PETg

Resistance:

1= stable, 2= conditionally stable, 3= unstable

Contents	Concentration	PETg	
		@20°C	@50°C
Acetaldehyde	40%	3	3
Acetic acid	10%	1	1
Acetic acid	5%	1	1
Acetic acid (glacial acetic acid)	90%	3	3
Acetic acid ester	100%	3	3
Acetone		3	3
Acetonitrile		-	3
Acid, battery	38%	3	3
Allyl alcohol	96%	1	-
Alum		1	1
Aluminium chloride	10%	1	1
Aluminium chloride	Aqueous	1	1
Aluminium nitrate	Aqueous	1	1
Aluminium sulfate	10%	1	1
Ammonia	25%	1	3
Ammonia liquor	Any	1	3
Ammonium chloride	Aqueous	1	1
Ammonium fluoride	Saturated	1	1
Ammonium fluoride	Aqueous	1	1
Ammonium nitrate	10%	1	1
Ammonium nitrate	Saturated	1	1
Ammonium nitrate	Aqueous	1	1
Ammonium sulfate	10%	1	1
Ammonium sulfate	Saturated	1	1
Ammonium sulfate	Aqueous	1	1
Amyl acetate (Pentylacetate)		1	2

Contents	Concentration	PETg	
		@20°C	@50°C
Amyl alcohol		1	-
Antifreeze (Ethleneglycol)		1	-
Aqua regia		3	3
Beer		1	-
Benzene		3	3
Benzoic acid	Saturated	1	-
Benzoic acid	Aqueous	1	-
Borax	Any	1	1
Boric acid	10%	1	-
Boric acid	Aqueous	1	-
Brake fluid DOT 3		1	1
Brandy		1	-
Bromic vapours		3	3
Bromine		3	3
Butane	Techn. Pure	1	-
Butanol	Techn. Pure	1	-
Butenediol	10%	1	-
Butyl acetate	Aqueous	2	-
Calcium chloride	Aqueous	1	-
Calcium hypochlorite	Aqueous	2	-
Calcium hypochlorite	Saturated	2	-
Calcium nitrate	50%	1	1
Calcium nitrate	Aqueous	1	1
Carbon dioxide, dry	Techn. Pure	1	1
Carbon dioxide, humid	Techn. Pure	1	1
Carbon tetrachloride		1	3
Carbonic acid	Saturated	1	1
Caustic potash	30%	3	3
Caustic potash	50%	3	3
Caustic potash	Aqueous	3	3
Caustic potash	10%	3	3
Caustic potash	50%	3	3
Caustic soda		3	3
Chlorinated water		3	3
Chlorine	10% wet	3	3
Chlorine	97%	3	3

Contents	Concentration	PETg	
		@20°C	@50°C
Chlorine gas		3	3
Chloroacetic acid		3	3
Chloroacetic acid (mono)	50%	3	3
Chloroacetic acid (mono)	Techn. Pure	3	3
Chlorobenzene		1	3
Chlorosulphonic acid	Techn. Pure	3	3
Chromic acid	10%	2	-
Chromic acid	20%	3	3
Chromic acid	50%	3	3
Chromic acid	Aqueous	3	3
Chromic alum	Saturated	1	1
Chromic sulphuric acid	Pure	3	3
Citric acid	10%	1	2
Citric acid	10%	1	2
Common salt		1	1
Common salt	Aqueous	1	1
Copper sulphate	Aqueous	1	1
Crude oil	100%	1	-
Cyclanone		1	1
Cyclohexane		1	-
Cyclohexanone	Techn. Pure	3	3
Dekalin (Decahydronaphthalin)	100%	2	-
Detergent solution		1	1
Dextrine		1	1
Dextrine	Aqueous	1	1
Dibutyl phthalate (DBP)		1	-
Dichloroethylene	Techn. Pure	3	3
Diesel oil	100%	1	1
Dimethyl formamide		1	-
Dioxane		1	-
Emissions, carbon dioxide	Low	1	1
Engine oil		1	1
Ethanol	50%	1	1
Ethanol	96%	1	1

Contents	Concentration	PETg	
		@20°C	@50°C
Ethyl acetate		2	3
Ethyl alcohol	40%	1	1
Ethyl alcohol	96%	1	1
Ethyl chloride		3	3
Ethylene glycol		1	-
Fat, vegetable		1	-
Fatty acid	Techn. Pure	1	-
Fertilizer salts	Saturated	1	-
Fluorhydric acid	100%	3	3
Fluorhydric acid	4%	3	3
Fluorhydric acid	50%	3	3
Fluorine		3	3
Fluorine	Dry	3	3
Formaldehyde	10%	1	-
Formaldehyde	40%	1	-
Formic acid	3%	1	-
Fruit juices		1	-
Fruit wine		1	1
Gelatine	Any	1	1
Gelatine	Aqueous	1	1
Glacial acetic acid		3	3
Glucose	Any	1	1
Glue (animal glue, gelatine)	Any	1	1
Glycerin	Any	1	-
Glykol		1	-
Grape sugar	Any	1	1
Grape sugar	Aqueous	1	1
Hexane		1	-
Hexane, -n		1	-
Hydrobromic acid		1	-
Hydrobromic acid	40%	3	3
Hydrobromic acid	50%	3	3
Hydrobromic acid	Diluted	2	-
Hydrochloric acid	1-5%	1	1
Hydrochloric acid	20%	2	-
Hydrochloric acid	35%	3	3
Hydrochloric acid	Conc.	3	3
Hydrofluosilicic acid	32%	3	3
Hydrogen fluoride	Anhydrous	3	3


Contents	Concentration	PETg	
		@20°C	@50°C
Hydrogene chloride gas		3	3
Hydrosulphide	Saturated	1	-
Isooctane	Techn. Pure	1	-
Kerosene		1	-
Kerosene		1	1
Lactic acid	3%	1	-
Lactic acid	Aqueous	1	-
Lead acetate	Aqueous	1	1
Lead-(II)-acetate		1	1
Linseed oil	Techn. Pure	1	-
Liqueurs		1	-
Lubricating oil		1	1
Magnesium sulphate	Saturated	1	1
Magnesium sulphate	Aqueous	1	-
Magnesium chloride	Aqueous	1	-
Mercury	Pure	1	1
Mercury chloride	Aqueous	1	1
Methanol		1	-
Methyl acetate	Techn. Pure	2	-
Methyl alcohol (methanole)		1	-
Methyl ethyl ketone		3	3
Methylen chloride		3	3
Milk		1	1
Molasses		1	-
Molasses Wort		1	1
Mowilith D		1	1
Nitric acid	100%	3	3
Nitric acid	1-10%	1	1
Nitric acid	50%	1	1
Nitric acid	66%	3	3
Nitric acid	70%	3	3
Oil (vegetable) and animal fats		1	-
Oleic acid	Techn. Pure	1	-
Oleum	10% SO3	3	3
Olive oil		1	-
Oxalic acid	Aqueous	1	1

Contents	Concentration	PETg	
		@20°C	@50°C
Palm-oil		1	-
Perchloric acid		3	3
Petrol		1	1
Petrol 10% ethyl alcohol		2	-
Petrol 10% methanol		2	-
Petrol normal		2	-
Petrol normal unleaded		2	-
Petrol Super unleaded		2	-
Petroleum		1	1
Phenol	100%	1	1
Phenol	10%	3	3
Phoshoric acid	1-5%	1	-
Photographic developers		1	-
Phthallic acid	Saturated	1	-
Plasticiser, DBS		1	1
Plasticiser, DOP		1	1
Potash	Saturated	1	1
Potash	Aqueous	1	1
Potassium bichromate	Saturated	2	-
Potassium borate	10%	1	1
Potassium borate	Aqueous	1	1
Potassium bromide	Any	1	1
Potassium chloride	Aqueous	1	-
Potassium hydroxide	50%	3	3
Potassium hydroxide	Conc.	3	3
Potassium hydroxide	Aqueous	3	3
Potassium hydroxide	10%	3	3
Potassium hydroxide	1%	3	3
Potassium nitrate	50%	1	1
Potassium nitrate	Aqueous	1	1
Potassium permanganate		1	1
Potassium permanganate	Aqueous	1	1

Contents	Concentration	PETg	
		@20°C	@50°C
Propane	Liquid	1	-
Propane	Gaseous	1	-
Propyl alcohol		1	-
Propyl alcohol	100%	1	-
Sea water		1	1
Silicic acid	Any	1	1
Silicone oil		1	-
Silver nitrate		1	1
Silver nitrate	Aqueous	1	1
Silver salt	Saturated	1	1
Soap solution	Any	1	1
Sodium carbonate	Aqueous	1	-
Sodium carbonate	Aqueous	1	-
Sodium chloride	Any	1	1
Sodium chloride	Aqueous	1	1
Sodium fluoride	Saturated	1	1
Sodium hydroxide	1%	2	2
Sodium hydroxide	50%	3	3
Sodium hydroxide	30%	3	3
Sodium hydroxide	45%	3	3
Sodium hydroxide	60%	3	3
Sodium hydroxide	Aqueous	3	3
Sodium hypochlorite		2	2
Sodium hypochlorite	12% Cl	2	2
Sodium hypochlorite	15%	2	2
Sodium hypochlorite	50%	3	3
Sodium hypochlorite	Saturated	3	3
Sodium hypochlorite	Diluted	2	2
Sodium hypochlorite	Aqueous	2	2
Sodium hypochlorite solution	20%	3	3
Sodium hypochlorite solution	50%	3	3

Contents	Concentration	PETg	
		@20°C	@50°C
Sodium hypochlorite solution	Diluted	2	-
Sodium nitrate	Saturated	1	1
Sodium nitrate	Aqueous	1	-
Sodium silicate	Aqueous	1	-
Sodium silicate	Any	1	-
Sodium sulfide	Aqueous	1	-
Spindle oil		1	-
Starch dilution	Any	1	1
Starch sirup		1	1
Stearic acid	Crystals	1	-
Styrene	100%	1	1
Sugar sirup		1	1
Sulphur	Techn. Pure	1	1
Sulphur trioxid		3	3
Sulphuric acid	40%	3	3
Sulphuric acid	60%	3	3
Sulphuric acid	80%	3	3
Sulphuric acid	95%	3	3
Sulphuric acid	Smoking	3	3
Tallow	Techn. Pure	1	-
Terpentine		1	1
Terpentine oil		1	-
Tetralin		1	-
Toluene		1	-
Transformer oil	100%	1	1
Trichlorethylene	100%	3	3
Triethanol amine	Techn. Pure	1	-
Urea	Aqueous	1	-
Urea	(Carbamide)	1	-
Urine		1	-
Water		1	1
Water, distilled/desalted		1	1
Wax alcohol	Techn. Pure	1	-
Wine vinegar		1	1
Wines		1	1
Yeast any		1	-
Zinc sulphate	10%	1	1

DOWNLOAD
OUR FREE APP



Brett Martin's plastic sheets product range includes extensive options in foam PVC, polycarbonate, PVC, acrylic, aPET, PETg, SAN and styrene.



Plastic Sheets

Head Office and Global Sales
Brett Martin Plastic Sheets
24 Roughfort Road,
Mallusk, Co. Antrim
Northern Ireland
BT36 4RB

Tel: +44 (0) 28 9084 9999
Fax: +44 (0) 28 9083 6666
Email: mail@brettmartin.com

For the latest information visit the company's web site:
www.brettmartin.com



Certificate No. 009125
BS EN ISO 9001 : 2008

All reasonable care has been taken in the compilation of the information contained within this literature. All recommendations on the use of our products are made without guarantee as conditions of use are beyond the control of Brett Martin. It is the customer's responsibility to ensure that the product is fit for its intended purpose and that the actual conditions of use are suitable. Brett Martin pursues a policy of continuous product development and reserves the right to amend specifications without prior notice. Foamalux® is a registered trademark of Brett Martin Ltd.